

Jinbo Marine

Marine & Offshore Equipment Datasheet

PRODUCT DATASHEET

MARINE DECK COVERING

Lightweight Primary Deck Covering

Main Specification No. Item name Index Standard 1 Initial setting time ≥ 1 h...

ISO9001 Supplier

Class Certificate

Export Supply



Key Highlights

Category	Marine Deck Covering
Standard	EN
Material	Dry material (A component):
Weight / Size	Item name Index Standard 1 Initial setting time ≥ 1 h Q/HCF1-2004 2 Final ...
Certificate	ABS,LR, BV, GL CCS

We can supply according to your requirement, drawings, class certificate needs, and delivery schedule.

Technical Specifications

Category	Marine Deck Covering	Model / SKU	Lightweight-Primary-Deck-Covering
Standard	EN	Material	Dry material (A component):
Weight / Size	Item name Index Standard 1 Initial setting time ≥ 1 h Q/HCF1-2004 2 Final setting time ≤ 12 h 3 Modulus of rupture ≥ 3 MPa 4 Compressive strength ≥ 10 MPa 5 Density ≤ 1300 kg/m ³ 6 Water absorption $\leq 10\%$ 7 Oil absorption $\leq 5\%$ 8 Heat conductivity ≤ 1.2 W/m.k 9 Not readily ignitability, smoke & toxicity In accordance with IMO.FTPC Parts 2,6/IMO.A 687(17) 10 Weight per square meter ≤ 16 kg/10mm/m ² Features Characteristic:	Certificate	ABS,LR, BV, GL CCS
Warranty	12 Months unless specified otherwise	Origin	China



0.040359s

CONTENTS

- China Lightweight Primary Deck Covering:
- Features
- Consume amount:

China Lightweight Primary Deck Covering:



Main Specification

No.	Item name	Index	Standard
1	Initial setting time	≥1h	Q/HCF1-2004
2	Final setting time	≤12h	
3	Modulus of rupture	≥3MPa	
4	Compressive strength	≥10MPa	
5	Density	≤1300kg/m ³	
6	Water absorption	≤10%	
7	Oil absorption	≤5%	
8	Heat conductivity	≤1.2W/m.k	
9	Not readily ignitability, smoke & toxicity	In accordance with IMO.FTPC Parts 2,6/IMO.A 687(17)	
10	Weight per square meter	≤16kg/10mm/m ²	

Features

Characteristic: Low density, strong adhesion, elastic, not water penetration, abrasion resistance.

Applied: Covering for not readily ignitable deck of cabins

Consume amount:

16 kg/m²

Packing: Dry material (A component): 20kg/pack; Liquid(B component): 8.5kg/barrel

Storage: Cool and dry place, moisture-proof, the quality guarantee period is 6 months

Certificate: ABS、 BV、 CCS、 DNV、 EC、 GL、 KR、 LR、 NK.

For more details, please feel free to contact us.

